

AD-A135 587

PHASE TRANSFORMATION STUDY OF CU₂S(U) OREGON STATE UNIV 1/1
CORVALLIS DEPT OF PHYSICS J A GARDNER ET AL. 01 SEP 83
TR-4 N00014-79-C-0668

UNCLASSIFIED

F/G 7/4

NL




END

FILED

1/1

DTIC



MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS-1963-A

2

AD-A135 587

OFFICE OF NAVAL RESEARCH/CHEMISTRY PROGRAM

Contract N00014-79-C-0668

Task No. NR 056-721

TECHNICAL REPORT NO. 4

Phase Transformation Study of Cu_2S .

by

John A. Gardner, D. K. Gaskill, M. Hirscher, H. Jaeger, K. S. Krane

and R. L. Rasera

Prepared for Publication

in the

Proceedings of the 1983 International Conference

on Hyperfine Interactions, Holland 1983

Oregon State University
Department of Physics
Corvallis, Or.

September 1, 1983

DTIC
ELECTE
DEC 8 1983
S D H

DTIC FILE COPY

Reproduction in whole or in part is permitted for
any purpose of the United States Government

DISTRIBUTION STATEMENT A

Approved for public release
Distribution Unlimited

PHASE TRANSFORMATION STUDY OF Cu_2S

John A. Gardner, D. K. Gaskill, M. Hirscher*, H. Jaeger, K. S. Krane, and R. L. Rasera**

Department of Physics, Oregon State University, Corvallis, OR 97331 USA

The phase transformations of crystalline Cu_2S in the temperature range 50°C to 600°C have been studied through electric quadrupole interactions of ^{111}Cd impurities observed by time-differential perturbed angular correlations. The Cd is subject to no discernable quadrupolar interaction in the cubic phase above 430°C . In the hexagonal phase between approximately 103°C and 430°C , a single-site, weakly temperature dependent, axially symmetric quadrupolar interaction is found. At lower temperature, the structure is complex with a number of different sites. These data were taken with a microcomputer-controlled TDPAC spectrometer with logical steering that allows a standard 4-detector spectrometer to collect simultaneously 12 channels of data.

1. Introduction

The crystal structures of copper-sulfur alloys near the Cu_2S composition have been difficult to determine. There are a number of distinct Cu_xS compounds between $x=1.8$ and $x=2.0$. [1,2] For Cu_2S , the crystal structure of two high temperature phases has been measured, but the exact structure of the complex monoclinic room temperature unit cell is not known. [3,4] The phase transition from the "high chalcocite" hexagonal phase to the complex "low chalcocite" phase occurs at 103.5°C for $x=2.000$ but is reported to drop to 90°C for the slightly more sulfur-rich compound with $x=1.990$. [2] Supercooling of the higher-T phase by as much as 20°C has also been noted. [2,5]

In this experimental study, the time differential perturbed angular correlation (TDPAC) spectra of gamma rays emitted by dilute ^{111}Cd impurities in Cu_2S are measured. [6] The Cd atoms apparently enter the lattice substitutionally for Cu. Above 430°C , the lattice is cubic, and copper nuclei are in sites which have zero electric field gradient. As expected, the angular correlation of the gamma rays emitted by Cd nuclei is unperturbed in samples above 430°C . Between approximately 103°C and 430°C , the lattice is hexagonal, and the Cd TDPAC spectrum is typical of an axially symmetric quadrupole interaction. Below 103°C , the

*Present address: Max-Planck Institut für Metallforschung, 7000 Stuttgart 80, W. Germany

**Permanent address: Department of Physics, University of Maryland Baltimore County, Baltimore MD

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER Technical Report #4	2. GOVT ACCESSION NO. AD-A135587	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) Phase Transformation Study of Cu ₂ S.		5. TYPE OF REPORT & PERIOD COVERED Interim
		6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) John A. Gardner, D. K. Gaskill, M. Hirscher, H. Jaeger, K. S. Krane and R. L. Rasera		8. CONTRACT OR GRANT NUMBER(s) N00014-79-C-0668
9. PERFORMING ORGANIZATION NAME AND ADDRESS Oregon State University Corvallis, OR 97331		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS NR-056-721
11. CONTROLLING OFFICE NAME AND ADDRESS Office of Naval Research/Chemistry Program Arlington, VA 22217		12. REPORT DATE September 1, 1983
		13. NUMBER OF PAGES 4
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		15. SECURITY CLASS. (of this report) Unclassified
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Approve for public release; distribution unlimited		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		<div style="border: 1px solid black; padding: 5px;"> Accession For NTIS GRA&I DTIC TAB Unannounced Justification By _____ Distribution/ Availability Code A-1 Avail and/or ial </div>
18. SUPPLEMENTARY NOTES To be published in Proceedings of the 1983 International Conference on Hyperfine Interactions, Holland 1983		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Cu ₂ S, time-differential perturbed angular correlations, phase transformations.		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) The phase transformations of crystalline Cu ₂ S in the temperature range 50°C to 600°C have been studied through electric quadrupole interactions studied through electric quadrupole interactions of ¹¹¹ Cd impurities observed by time-differential perturbed angular correlations. The Cd is subject to no discernable quadrupolar interaction in the cubic phase above 430°C. In the hexagonal phase between approximately 103°C and 430°C, a single-site, weakly temperature dependent, axially symmetric quadrupolar interaction is found. At lower temperature, the structure is complex with a number of different sites. These data were taken		

DD FORM 1473
1 JAN 73

EDITION OF 1 NOV 65 IS OBSOLETE
GPO 5102-LP-014-0001

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

83 12 08 025

Block 20 (continued)

→ with a microcomputer-controlled TDPAC spectrometer with logical steering that allows a standard 4-detector spectrometer to collect simultaneously 12 channels of data. ←

Accession for

DATE

DATE

DATE

spectrum is complex and both time- and sample-dependent. It is clear that in order to attain good thermal equilibrium, the low-temperature samples should be annealed considerably longer than the tracer decay time allows. Even though the equilibrium TDPAC spectrum cannot be readily measured in the room-temperature phase, the spectra of nonequilibrium samples provide some insight into its structure.

2. Experimental apparatus and procedure

Samples were made by sealing carefully weighed quantities of 99.999% purity copper and 99.99% purity S into quartz capsules, heating above the melting point of copper, and mixing for an hour or more before cooling. Since Cu_2S is reported to dissolve small amounts of sulfur but very little copper [2], samples were made very slightly Cu-rich. This was done to ensure that the sample was nearly stoichiometric Cu_2S with small inclusions of copper. The latter is cubic and more-or-less irrelevant in a TDPAC experiment. Approximately 0.05 cm^3 of this material was placed in a thin quartz sample capsule to which a few drops of $^{111}\text{In}/\text{HCl}$ solution were added. After drying, the capsule was sealed in vacuum and heated until the In had diffused well into the sample before any data were taken.

The TDPAC spectrometer consists of four NaI(Tl) scintillation counters arranged in fixed positions at 90 degree intervals in the horizontal plane around the sample furnace. Delayed coincidences of the two gamma rays are detected at interdetector angles of 90 and 180 degrees by a variation of standard fast-slow coincidence methods. Any counter can detect the first photon of the cascade and any of the other three can detect the second. The number of coincidences for any of the twelve possible counter pairs is counted, typically for 12 to 24 hours, as a function of time t between the two gamma emissions and stored in a microcomputer memory. Sample temperature is maintained by a small nichrome-wound water-cooled furnace.

Data are analyzed by forming the ratio

$$R'(t) = \frac{2}{3} \left\{ \left(\frac{2 C_{20}C_{31}C_{02}C_{13}}{C_{10}C_{21}C_{32}C_{03} + C_{30}C_{01}C_{12}C_{23}} \right)^{1/4} - 1 \right\} \quad (1)$$

$$R(t) \equiv A_{22}G_2(t) = R'(t)/[1 + 0.5R'(t)] \quad (2)$$

where $C_{ij}(t)$ is the coincidence count rate when counter i detects the first and counter j the second gamma ray. Counters are numbered consecutively so $C_{01}, C_{10}, C_{12}, C_{21}$, etc. are 90° and C_{02}, C_{20}, C_{13} , and C_{31} are 180° coincidences. A more complete description of the spectrometer and data analysis methods will be published elsewhere.

Each type α of Cd site contributes a term,

$$R_a(t) = A_{22} \left(S_0 + \sum_{i=1}^3 S_i \cos(\omega_i t) e^{-(\omega_i t \delta)^2 / 2} \right) \quad (3)$$

where the frequencies ω_i are determined by the electric field gradient (EFG), and the geometrical factors S_i depend on the orientation of the EFG principal axes. The damping parameter δ arises from the spread of frequencies in imperfect crystals. The complete $R(t)$ is the sum of such terms, weighted by the probability of occurrence.

3. Experimental results and conclusions

In the hexagonal phase, $R(t)$ could be fit to a slightly-damped single-site axially-symmetric quadrupole interaction. Typical $R(t)$ spectra are shown in Fig. 1. Damping was somewhat sample-dependent and increased with decreasing temperature near the transition temperature. Damping may be due to slight departures from stoichiometry at low temperature where excess sulfur is soluble. The quadrupole frequency vs. T is given in Fig. 2.

Figure 1 also shows a typical $R(t)$ for a sample below the monoclinic/hexagonal transition temperature. Monoclinic-phase spectra could not be well fit by either a single-site or 2-site interaction with moderate damping. A "2-site" computer fit in which one site was highly damped did describe the data reasonably well however. Approximately half the nuclei are in "good" sites having a quadrupole frequency $\nu_Q = 119(6)$ MHz and asymmetry parameter $\eta = 0.37(7)$. The highly damped portion apparently arises from nuclei in a number of different sites or from sites where the electric field gradient changes significantly during the data accumulation time.




Figure 1. $R(t)$ for dilute ^{111}Cd impurities in Cu_2S , hexagonal phase at 136°C (right) and monoclinic phase at 100°C (left). The full lines are computer fits to (right) a single-site axially symmetric quadrupolar interaction and (left) a 2 site model with one site subject to a slightly damped nonaxially-symmetric quadrupolar interaction, and the second "site" greatly damped.




Figure 2. Quadrupolar frequency vs. T for ¹¹¹Cd impurities in hexagonal phase Cu₂S.

ACKNOWLEDGEMENTS

This research was supported in part by the US Office of Naval Research.

REFERENCES

- [1] M. Hansen, The Constitution of Binary Alloys, (McGraw-Hill, New York, 1958) p. 620.
- [2] R. W. Potter II, Economic Geology **72** (1977) 1524.
- [3] R. W. Potter II and H. T. Evans, Jr., Jour. Research US Geol. Survey **4** (1976) 205.
- [4] H. T. Evans, Jr., Phys. Sci., **232** (1971) 69.
- [5] B. J. Mulder, Kristall und Technik **8** (1973) 825.
- [6] H. Frauenfelder and R. M. Steffen, in Perturbed Angular Correlations, ed. by E. Karlsson, E. Matthias, and K. Siegbahn (North Holland, Amsterdam, 1963).

TECHNICAL REPORT DISTRIBUTION LIST, GEN

	<u>No. Copies</u>		<u>No. Copies</u>
Office of Naval Research Attn: Code 413 800 North Quincy Street Arlington, Virginia 22217	2	Naval Ocean Systems Center Attn: Mr. Joe McCartney San Diego, California 92152	1
ONR Pasadena Detachment Attn: Dr. R. J. Marcus 1030 East Green Street Pasadena, California 91106	1	Naval Weapons Center Attn: Dr. A. B. Amster, Chemistry Division China Lake, California 93555	1
Commander, Naval Air Systems Command Attn: Code 310C (H. Rosenwasser) Department of the Navy Washington, D.C. 20360	1	Naval Civil Engineering Laboratory Attn: Dr. R. W. Drisko Port Hueneme, California 93401	1
Defense Technical Information Center Building 5, Cameron Station Alexandria, Virginia 22314	12	Dean William Tolles Naval Postgraduate School Monterey, California 93940	1
Dr. Fred Saalfeld Chemistry Division, Code 6100 Naval Research Laboratory Washington, D.C. 20375	1	Scientific Advisor Commandant of the Marine Corps (Code RD-1) Washington, D.C. 20380	1
U.S. Army Research Office Attn: CND-AA-IP P. O. Box 12211 Research Triangle Park, N.C. 27709	1	Naval Ship Research and Development Center Attn: Dr. G. Bosmajian, Applied Chemistry Division Annapolis, Maryland 21401	1
Mr. Vincent Schaper STNSDC Code 2803 Annapolis, Maryland 21402	1	Mr. John Boyle Materials Branch Naval Ship Engineering Center Philadelphia, Pennsylvania 19112	1
Naval Ocean Systems Center Attn: Dr. S. Yamamoto Marine Sciences Division San Diego, California 91232	1	Mr. A. M. Ansalone Administrative Librarian PLASTEC/ARRADCOM Bldg 3401 Dover, New Jersey 07801	1

TECHNICAL REPORT DISTRIBUTION LIST, 056

	<u>No. Copies</u>		<u>No. Copies</u>
Dr. G. A. Somorjai Department of Chemistry University of California Berkeley, California 94720	1	Dr. W. Kohn Department of Physics University of California (San Diego) La Jolla, California 92037	1
Dr. J. Marday Naval Research Laboratory Surface Chemistry Division (6170) 455 Overlook Avenue, S.W. Washington, D.C. 20375	1	Dr. R. L. Park Director, Center of Materials Research University of Maryland College Park, Maryland 20742	1
Dr. J. B. Hudson Materials Division Rensselaer Polytechnic Institute Troy, New York 12181	1	Dr. W. T. Peria Electrical Engineering Department University of Minnesota Minneapolis, Minnesota 55455	1
Dr. Theodore E. Madey Surface Chemistry Section Department of Commerce National Bureau of Standards Washington, D.C. 20234	1	Dr. Chia-wei Woo Department of Physics Northwestern University Evanston, Illinois 60201	1
Dr. J. M. White Department of Chemistry University of Texas Austin, Texas 78712	1	Dr. Robert M. Hexter Department of Chemistry University of Minnesota Minneapolis, Minnesota 55455	1
Dr. Keith E. Johnson Department of Metallurgy and Materials Science Massachusetts Institute of Technology Cambridge, Massachusetts 02139	1	Dr. R. P. Van Duyne Chemistry Department Northwestern University Evanston, Illinois 60201	1
Dr. J. E. Demuth IBM Corporation Thomas J. Watson Research Center P. O. Box 218 Yorktown Heights, New York 10598	1	Dr. S. Sibener Department of Chemistry James Franck Institute 5640 Ellis Avenue Chicago, Illinois 60637	1
Dr. G. P. Flynn Department of Physics University of Illinois Urbana, Illinois 61801	1	Dr. M. G. Lagally Department of Metallurgical and Mining Engineering University of Wisconsin Madison, Wisconsin 53706	1

TECHNICAL REPORT DISTRIBUTION LIST, 056

	<u>No. Copies</u>		<u>No. Copies</u>
Dr. Robert Comer Department of Chemistry James Franck Institute 5000 Ellis Avenue Chicago, Illinois 60637	1	Dr. K. G. Spears Chemistry Department Northwestern University Evanston, Illinois 60201	1
Dr. R. G. Wallis Department of Physics University of California, Irvine Irvine, California 92664	1	Dr. R. W. Plummer University of Pennsylvania Department of Physics Philadelphia, Pennsylvania 19104	1
Dr. D. Ruckner Chemistry Department George Washington University Washington, D.C. 20052	1	Dr. E. Yeager Department of Chemistry Case Western Reserve University Cleveland, Ohio 44106	1
Dr. P. Rappaport Physics Department University of California, Santa Barbara Santa Barbara, California 93106	1	Professor D. Hercules University of Pittsburgh Chemistry Department Pittsburgh, Pennsylvania 15260	1
Dr. J. C. Swearingen Chemistry Department University of California, Irvine Irvine, California 92717	1	Professor N. Winograd The Pennsylvania State University Department of Chemistry University Park, Pennsylvania 16802	1
Dr. Robert W. Fessenden Department of Chemistry London University London, England	1	Professor T. F. George The University of Rochester Chemistry Department Rochester, New York 14627	
Dr. J. Watson Department of Chemistry University of California, Santa Barbara Santa Barbara, California 93106	1	Professor Dudley R. Herschbach Harvard College Office for Research Contracts 1330 Massachusetts Avenue Cambridge, Massachusetts 02138	1
Dr. J. Watson Research Center P. O. Box 718 Watson Heights, New York 10598	1	Professor Horia Matiu University of California, Santa Barbara Chemistry Department Santa Barbara, California 93106	
Dr. J. Watson Department of Physics University of California, Santa Barbara Santa Barbara, California 93106	1	Prof. A. Steckl Rensselaer Polytechnic Institute Department of Electrical and Systems Engineering Integrated Circuits Laboratories Troy, New York 12181	

TECHNICAL REPORT DISTRIBUTION LIST, 056

No.
Copies

No.
Copies

Dr. John T. Yates
Department of Chemistry
University of Pittsburgh
Pittsburgh, Pennsylvania 15260

Professor G. H. Morrison
Department of Chemistry
Cornell University
Ithaca, New York 14853

Captain Lee Myers
AFOSR/NC
Bolling AFB
Washington, D.C. 20332

Dr. David Squire
Army Research Office
P. O. Box 12211
Research Triangle Park, NC 27709

Professor Ronald Hoffman
Department of Chemistry
Cornell University
Ithaca, New York 14853

END

FILMED

1-84

DTIC